



PRIME 3000

PRIME 3000 is a Polypropylene Copolymer thermoplastic sheet designed for automotive, leisure, transportation & general thermoforming and fabrication applications. PRIME 3000 has a high impact resistance, especially at ambient temperatures & excellent chemical resistance.

	Property	Unit	ISO	Value
PHYSICAL				
Density		g/cc	1183	.91
Melt Flow (230°C/2.16kg)		g/10min	118	0.3
MECHANICAL				
Izod Impact, notched	kJ/m ²	23°C	180/A	58
		-30°C	180/A	7
Strength @ yield	MPa	50mm/min	527/2	28
Strain @ yield	%	50mm/min	527/2	12
Tensile Modulus Flexular	MPa		527/2	1300
Modulus	MPa		178	1350
Shore D surface hardness			868	64
Glass transition	°C			-18
Water absorption	%		24 hrs	0.01
THERMAL				
VST @ 10N (VST/A)	°C		306/A	158
HDT@0.45 MPa (HDT/B)CLTE	°C		75/B	90
Thermal cond.	cm/(cm °C)		ASTM D570	7.5 x 10 ⁻⁵
	W/m/K°			1.0
FLAMABILITY RATING³				
Horizontal burn	1.5mm		UL94	HB
	3mm		UL94	HB
Typical forming temp	°C			140-180

Finishing

Aluminium tool construction is recommended with a temperature control function to ensure consistent moulding & finished part dimensional tolerances. A constant tool temperature (Typically 70-80°C for PRIME 3000) should be maintained throughout the production run. Cooling using air or water spray will speed up the cooling cycle to provide efficient production output. Once removed from the tool, it is recommended that the component is clamped in a frame for a short period to optimise dimensional stability & reduce the risk of warping.

Colour, Textures, Capabilities

PRIME 3000 is available in a full range of colours (subject to minimum order quantities) either colour matched to specific colour references, or to customer sample. A range of more standard colours is available for non-specific requirements. For outdoor use, PRIME 3000 can be stabilised against UV degradation. PRIME3000 is available with a smooth or with a textured finish. Emboss swatches are available on request.

Notice: All statements, information, and data given herein are believed to be accurate and reliable but are presented without guarantee, warranty, or responsibility of any kind, expressed or in implied. Statements or suggestion concerning possible use of our products are made without presentation of warranty that such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated. or that other measures may not be required.