PRIMEX

European Division

PRIME 6000

Our Prime 6000 is a general-purpose ABS (Acrylonitrile-Butadiene-Styrene) sheet product designed for automotive, leisure, transportation, and general thermoforming applications..

Offers good impact strength, and good hot strength for thermoforming.



Customisation

All Primex grades are formulated with the user in mind, and various modifications for products are possible.

Primex has a PRIME grade suitable for your application. Please get in touch with your usual Primex contact to discuss

Prime 6000 ABS can be colour matched to meet your specific requirements.



Sustainability

Sustainability includes considering the product's circularity or end of life during the design of the finished product. Prime 6000 ABS (recycle code 7) can be recycled as a post-industrial or post-consumer product..

Primex Sustainability: A better tomorrow, starting today!



For more information on any of our materials,
please contact us.

+44(0) 1325 315 768 | primexplastics.co.uk

PRIME 6000 ABS | Data Sheet

Prime 6000 ABS is an amorphous thermoplastic material and therefore, processes easier than some other thermoplastic materials.

Property	Standard	Unit	Value
Melt Volume Rate 220 °C/10 kg	ISO 1133	cm^3/10 min	6
Charpy Notched Impact Strength, 23° C	ISO 179/1eA	kJ/m^2	32
Charpy Notched Impact Strength, -10° C	ISO 179/1eA	kJ/m^2	17
Charpy Notched Impact Strength, -30° C	ISO 179/1eA	kJ/m^2	12
Tensile Stress at Yield, 23 °C	ISO 527	MPa	40
Tensile Strain at Yield, 23 °C	ISO 527	%	2.6
Tensile Stress at Break, 23 °C	ISO 527	MPa	31
Tensile Strain at Break, 23 °C	ISO 527	%	28
Tensile Modulus	ISO 527	MPa	2000
Hardness, Rockwell	ISO 2039-2	R scale	107
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	96

Applications

Prime 6000 ABS may be used for interior applications such as appliance parts, tub/shower surrounds, pick-up truck caps, boat accessories, and automotive trim parts. With the addition of a weatherable cap it may also be used in many outdoor application.

Finishing

Prime 6000 ABS may be joined with machine screws, bolts, nuts, rivets, and spring steel fasteners. Thread cutting or thread-forming screws is an economical means of securing separate joints. Formed parts may be joined with Methylene Chloride if maximum impact strength is not required. Press and snap techniques, and sonic welding may also be used for the bonding of Prime 6000 ABS.

Colours, Textures, and Capabilities

Prime 6000 ABS is available in thicknesses from 1mm-8mm. Textures include; pinseal, and smooth.

Prime 6000 ABS	Very High	High	Avg.
Impact Strength		*	
Low Temperature Impact Strength			*
Tensile Strength		*	
Flexural Modulus		*	
Heat Deflection Temperature		*	

Notice: All statements, information, and data given herein are believed to be accurate and reliable but are presented without guarantee, warranty, or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation of warranty that such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required.